

Ultrafix SB3 Plus

APPLICATIONS

Frame adhesive

GENERAL CHARACTERISTICS

- Two-component polyurethane adhesive
- Long mixed pot life—more than 7 days in a sealed container
- Mounts screen mesh onto aluminum, steel, iron, plastic-coated, and wood frames
- Extraordinary initial adhesion allows screens to be removed from the stretching system only minutes after applying
- Superior resistance to solvents, heat, and automatic cleaning machines
- SaatiChem Ultrafix SB3 is a clear, low viscosity adhesive for high to medium mesh counts

DIRECTIONS FOR USE

Mix 50 parts of Ultrafix SB3 Plus adhesive with 1 part of Catalyst by weight. Mixed adhesive pot-life is maintained for a minimum of 48 hours when stored in an airtight container. To obtain optimal adhesion,

decrease the frame. Stretch the fabric over the frame providing good contact between the two. Apply the prepared mixture with a brush. After the adhesive has dried and cured, release tension and remove the screen from the stretching system.

Health & Safety

Before using, refer to appropriate material safety data sheets.

STORAGE

When sealed in the original container and stored in cool conditions, SaatiChem products will maintain their original properties for one year from the date of production.

PACKAGING

Ultrafix SB3 Plus and Catalyst are available in one gallon kit.

WARRANTY & LIMITED REMEDY

The directions, recommendations, and specifications contained in this Technical Data Sheet are meant as a guide to the use of the product and shall not bind the company. Product specifications are subject to change without notice.

The following is made in lieu of all other expressed or implied warranties, including any implied warranty of merchantability or fitness for a particular purpose:

All SaatiChem manufactured liquid products are warranted to be free of defects in materials and manufacture and to meet the specifications stated in SaatiChem's applicable Product Bulletin. SaatiChem will replace or refund the price of any SaatiChem manufactured liquid product that does not meet this warranty within the applicable warranty period.

The remedies are exclusive. In no case shall SaatiChem be liable for any other direct or indirect damage or loss, including without limitation any incidental, special, or consequential damages, or any material costs or labor charges incident to the removal or replacement of any mesh, screen, ink, substrate, finished graphic or any other item.

To receive the Material Safety Data Sheet (MSDS), send an e-mail to: MSDS@saatichem.com

USA

1.877.296.7697 [Toll-free US & Canada]
or 1.847.296.7697
e-mail: info.US@saatichem.com

Italy

+39.031.9711
e-mail: info.IT@saatichem.com

China

+86.21.58999113
or +86.21.58349020
e-mail: info.CN@saatichem.com

For More Information

about SaatiChem
visit our website:
www.saatiamericas.com