

# Saatifil® Polypropylene

PRODUCT NUMBER	Mesh Opening	Open Area	Mesh Count		Thread Diameter	Weight		Thickness	Air Permeability @ 20 mm WG
	[µm]	[%]	[n/cm]	[n/inch]	[µm]	[g/m²]	[oz/sq.yd]	[µm]	[l/m²s]
● PP 980/47	980	47	7	18	490	250	7.37	960	7900
● PP 500/36	500	36	12	30	320	180	5.31	690	8175
PP 460/47	460	47	15	38	200	92	2.71	390	9000
PP 350/32	350	32	16.7	42	250	172	5.07	525	6500
PP 300/21	300	21	15	38	320	230	6.78	700	5800
PP 297/35	297	35	20	51	200	125	3.69	420	6650
● PP 230/27	215	23	22	56	200	142	4.19	340	5125
PP 210/32	210	32	27.5	70	150	98	2.89	315	7225
PP 100/23	100	23	47	119	100	75	2.21	225	5075

● routinely produced **PP** = Polypropylene

The technical specifications listed, with the exception of the thread diameter, are nominal values and are based on the arithmetic mean value of production samples. In accordance with our policy of continuously improving our products, the above listed technical specifications are subject to change without notice.

#### USA Headquarters

USA Saati Americas Tel: (+1) 914 767 0100 Fax: (+1) 914 767 0109 E-mail: info.US@saatitech.com

#### World Headquarters

ITALY Saati S.p.A. Tel: (+39) 031 9711 Fax: (+39) 031 933392 E-mail: info.IT@saatitech.com

#### Branches

FRANCE Saati France S.a.S. Tel: (+33) 3 22857700 Fax: (+33) 3 22857709 E-mail: info.FR@saati.com

GERMANY Saati GmbH Tel: (+49) 711 5103015 Fax: (+49) 711 5103017 E-mail: info.DE@saati.com

BRAZIL Saati do Brasil IMP.EXPLTDA. Tel: (+55) 19 34241442 Fax: (+55) 19 34242594 E-mail: info.BR@saati.com

CHINA Shanghai Saati Fabrics Co. Ltd. Tel: (+86) 21 58999113 Fax: (+86) 21 50317438 E-mail: info.CN@saati.com



[www.saatiamericas.com](http://www.saatiamericas.com)

 SAATIgroup™